NorGeoSpec 2012 Product Certificate

Quality Product Certification Reinforcement

This product has been found to be fit for use in accordance with NorGeoSpec 2012 System for the above given function.

Certificate no.:	NGS-50344
Date:	01.08.2023
Valid until:	31.07.2025
Manufacturer:	TenCate Geosynthetics Austria GmbH
Product:	Miragrid GX 110/30
Product Type:	GGR
Raw material:	PET
Function:	Reinforcement

Issued by

Austr- leves

Christian Recker, SINTEF project manager

Approved by



Arnstein Watn, Head of the Technical committee

The products are regularly audited and tested to verify that the characteristics fulfil the NorGeoSpec 2012 Rev.: 01/14.12.2016 requirements. Approved by the NorGeoSpec Technical committee: 22.05.2023



Quality Product Certification Reinforcement

Characteristic		Standard	Unit	Declared value	Declared tolerance	Max. tolerance	Certification value	
Mass per unit area		EN ISO 9864	g/m²	422	± 42.2	± 42.2	379.8 – 464.2	
Dimension		NorGeoSpec 2012						
Tensile elements	MD	Annex F	Production width ¹	210	± 0	± 0	210	
	CMD	Annex F	Elements/m	35.0	± 2.1		32.9 – 37.1	
Grid apertures	MD	Annex F	mm	19	± 2.8	± 2.9	16.2 – 21.8	
	CMD	Annex F	mm	25	± 3.8	± 3.8	21.2 – 28.8	
Mechanical tests								
Nominal tensile strength	MD	EN ISO 10319	kN/m	116.00	-5.80	-5.80	110.20	
	CMD	EN ISO 10319	kN/m					
Tensile strain at nominal strength	MD	EN ISO 10319	%	10.5	± 2.1	± 2.1	8.4 – 12.6	
	CMD	EN ISO 10319	%					
Tensile stiffness at 2% tensile strain	MD	EN ISO 10319	kN/m	1000	- 200.0	- 200.0	800	
	CMD	EN ISO 10319	kN/m					
Tensile stiffness at 5% tensile strain	MD	EN ISO 10319	kN/m	700	- 140.0	- 140.0	560	
	CMD	EN ISO 10319	kN/m					
Tensile stiffness at 10% tensile strain	MD	EN ISO 10319	kN/m					
	CMD	EN ISO 10319	kN/m					
Static puncture test		EN ISO 12236	KN					
Dynamic perforation resistance		EN ISO 13433	mm					
Durability (Declared value)								
Service life		years	25		50	100		

¹ Production width – 5.20 m



Declared values Reinforcement

Declared values									
Reduction factor for creep rupture ^{1) 2)}	RF _{CR} 1.58 KIWA test report: 1.6/24520/0354.0.1-2019e								
Reduction factor for environmental effects	RF _{CH}								
Chemical				Application in natural soils at a pH-value between 4 and 9 and a soil temperature <25°C					
Oxidation		n.r.							
Hydrolysis		1.04	SKZ test report:	SKZ test report: 89363/09-II					
Reduction factor for weathering	RFw								
Or max. exposure time									
1 month		х							
2 weeks									
1 day									
Reduction factor for installation damage	RF _{ID,fine}	1.10	$RF_{ID,medium}$	1.14	RF _{ID coarse}	1.11			
Used test method	Baugrund W	Baugrund Wien 10-2022-01							
Compaction		Min. compaction depth above geogrid 320 mm; Ride-on steel-wheeled roller (12400 kg); Relative density > 9							
Particle size	$RFI_{D medium} = 0$	$\label{eq:RF_ID_fine} \begin{split} & RF_{ID_fine} = slightly plastic clay, slightly sandy with D_{90} = 1.5 \text{ mm and } D_{60} = 0.06 \text{ mm} \\ & RFI_{D_medium} = crushed lime - / \text{ dolomite rock with } D_{90} = 26 \text{ mm and } D_{60} = 11 \text{ mm} \\ & RF_{ID_coarse} = crushed concrete with D_{90} = 63 \text{ mm and } D_{60} = 28 \text{ mm} \end{split}$							